

Gredmann Group

台灣格雷蒙股份有限公司

偉斯企業股份有限公司

9F, No. 170 Sec. 3, Min Chuan East Road, Taipei, Taiwan

Tel : 886-2-2719-3456 (20 lines) Fax : 886-2-2716-5500 (3 Lines)

Web Site : www.gredmann.com

EVA Encapsulation Film

| Specification | Unit | Testing Method | Value |
|--------------------------------------|--------------------|----------------|--------------------------|
| Surface finish | | | Double side Embossing |
| Density | g/cm ³ | ASTM D1505 | 0.950 |
| VA content | % | FPC method | 28.0 |
| Gel content | % | FPC method | 85 |
| UV cutoff wave lenth | nm | FPC method | 360 |
| Water absorption | % | ASTM D570 | 0.1 |
| Hardness | Shord D | ASTM D2240 | 26 |
| Tensile strength at break | Kg/cm ² | ASTM D638 | 80 |
| Elongation at break | % | ASTM D638 | > 800 |
| Adhesion to glass | N/cm | FPC method | > 60 |
| Adhesion to Tedlar | N/cm | FPC method | > 60 |
| Optical transmission (280-1100nm) | % | UV-VIS | > 91 |