

Gredmann Group

台灣格雷蒙股份有限公司

偉斯企業股份有限公司

9F, No. 170 Sec. 3, Min Chuan East Road, Taipei, Taiwan

Tel : 886-2-2719-3456 (20 lines) Fax : 886-2-2716-5500 (3 Lines)

Web Site : www.gredmann.com

Silicon Carbide(SiC)

Application: Sawing Powder in the wafer slicing process

Specification	Particle Distribution (um)			Chemical Content (%)		
	D3	D50	D94	SIC	Fe ₂ O ₃	F.C
GC-JIS800	≤31.0	14.0-15.0	≥9.5	≥98.5	≤0.2	≤0.2
GC-JIS1000	≤19.0	11.3-11.8	≥7.5	≥98.5	≤0.2	≤0.2
GC-JIS1200	≤16.0	9.8-10.4	≥6.3	≥98.5	≤0.2	≤0.2
GC-JIS1500	≤14.0	7.8-8.4	≥5.0	≥98.5	≤0.2	≤0.2
GC-JIS2000	≤12.0	6.0-7.0	≥4.0	≥98.0	≤0.2	≤0.2