

To:

**KIMOTO KB FILM Technical Data Sheet**

## ◎ Type

**KB FILM 125、188GSCWM**

## ◎ Recommended applications

- Lower electrode for T/P
- Cover for Display

## ◎ Structure

25 $\mu$ PET protection
Clear HC
125 or 188 $\mu$ PET
Clear HC
50 $\mu$ PE protection

## ◎ Properties

Properties	Item	Unit	Method	Equipment	125 GSCWM	188 GSCWM
Optical	Total Light Transmittance	%	JIS K 7361	Nippon Denshoku	91.5	91.4
	HAZE	%	JIS K 7136	Nippon Denshoku	0.1	0.2
Hardness	Pencil Hardness	Mitsubishi	JIS K 5400	Hardness tester	3H	3H
	SteelWool abrasion	—	200g/2cm <sup>2</sup> 10 rubs	SW#0000	No Scratch	No Scratch
Physical	Tape adhesion	O/100	Cross cut peeling	-	100/100	100/100

※ The test data represented in this document is for reference only and should be regarded as a guideline for use.